

Specification Text

Individual design
ISOLAR®
Dekorex



Product Characteristic

Laminated safety glass with metallic coating according project-specific drawing. Resistance to weathering such as abrasion, acidity and condensation. Meeting the requirements of EN 1096-2 Class A.

Laminated Safety Glass acc. EN 12543

Dekorex oHT chrome (70% BDG)

Laminated Safety Glass (from the outside to inside):

Single glass thickness / - type: (or

nominal thickness)

6:6.2 mm

Coating:

decodesign oHT chrome (70% BDG)

Coating position:

2

Total thickness of insulated glass unit 13 mm

(total thickness made up by nominal thickness and IGU gap)

Glass thicknesses according to static requirements

Technical values according to EN410/EN673:

The following technical values must at least be specified (vertical installation):

Product name

Dekorex oHT chrome (70% BDG)

Heat transfer coefficient (U_g):

5.4 W/(m²K) acc. EN 673

Light transmission:

30% acc. EN 410

Light reflection outside:

37% acc. EN 410

Solar Heat Gain (g-value):

36% acc. EN 410

Sound insulation R_{w,p}:

37 db acc. EN ISO 717-1

Deviating technical values resulting from other glass thicknesses or glass types shall be communicated to the Contractor.

1) Technical data for monolithic make-ups are approximate. Please contact us for more details.

Amount:

Unitt: sqm

Nov-20